

TECHNICAL DATA SHEET

EUROBENT CS-0,2

Mechanically bonded composite, consisting of pulverized or granulated bentonite, embedded and fixed between two layers of geo-textile and glued to a membrane.

Mass per unit area (average)

Carrier Layer	PP Woven	100 g/m ²
Inlay	Na-Bentonite	4.000 g/m ²
Cover Layer	PP Nonwoven	200 g/m ²
	PE Membrane	0,2 mm
Total Product Weight	ASTM D 5993	4.500 g/m ² (+/- 10 %)

Bentonite Properties

Montmorillonite Content	CUR 33	≥ 75 %
Swelling Capacity	ASTM D 5890	> 24 ml/2g
Moisture Content	DIN 18121-1 / 18121-2	max 12 %

Physical Properties of the Composite

Thickness	EN ISO 9863-1 / 9863-2	6,8 mm
Index Flux	ASTM D 5887	NOT MEASUREABLE
Permeability	ASTM D 5887	NOT MEASUREABLE
Tensile Strength	MD EN ISO 10319	10,4 kN/m (- 10 %)
	CD EN ISO 10319	10,4 kN/m (- 10 %)
CBR Puncture Strength	EN ISO 12236	1,8 kN (- 10 %)
Peel Strength	ASTM D 6496	60 N/10 cm (- 10 %)

Durability:

-cover in installation day

-durability 25 years at natural base and pH between 4 and 9 and temperature < 25°C.

Standard Roll Dimensions	Length / Width	(40 x 5,0) m
---------------------------------	----------------	---------------


These data are average values derived from standard tests and are subject to usual product variation. The right is reserved to make changes without notice at any time.

Poland 58-100 Świdnica, ul. Kliczkowska 42

+48 510 255 205; +48 74 857 50 81

+48 512 054 215

 www.eurobent.com

 office@eurobent.com