

## TECHNICAL DATA SHEET

### EUROBENT CS-0,6

Mechanically bonded composite, consisting of pulverized or granulated bentonite, embedded and fixed between two layers of geotextile and glued to a membrane.

#### Mass per unit area (average)

Carrier Layer	PP Woven	100 g/m <sup>2</sup>
Inlay	Na-Bentonite	4.000 g/m <sup>2</sup>
Cover Layer	PP Nonwoven	200 g/m <sup>2</sup>
	PE Membrane	0,6 mm
Total Product Weight	ASTM D 5993	4.900 g/m <sup>2</sup> ( +/- 10 % )

#### Bentonite Properties

Montmorillonite Content	CUR 33	≥ 75 %
Swelling Capacity	ASTM D 5890	> 24 ml/2g
Moisture Content	DIN 18121-1 / 18121-2	max 12 %

#### Physical Properties of the Composite

Thickness	EN ISO 9863-1 / 9863-2	7,2 mm
Index Flux	ASTM D 5887	NOT MEASUREABLE
Permeability	ASTM D 5887	NOT MEASUREABLE
Tensile Strength	MD EN ISO 10319	15,4 kN/m ( - 10 % )
	CD EN ISO 10319	15,4 kN/m ( - 10 % )
CBR Puncture Strength	EN ISO 12236	2,5 kN ( - 10 % )
Peel Strength	ASTM D 6496	60 N/10 cm ( - 10 % )

#### Durability:

-cover in installation day

-durability 25 years at natural base and pH between 4 and 9 and temperature < 25°C.

<b>Standard Roll Dimensions</b>	Length / Width	( 40 x 5,1) m
---------------------------------	----------------	---------------


These data are average values derived from standard tests and are subject to usual product variation. The right is reserved to make changes without notice at any time.

Poland 58-100 Świdnica, ul. Kliczkowska 42

+48 510 255 205; +48 74 857 50 81

+48 512 054 215

 [www.eurobent.com](http://www.eurobent.com)

 [office@eurobent.com](mailto:office@eurobent.com)