

EUROBENT Sp. z o.o. Kliczkowska 42 PL-58-100 Świdnica	TECHNICAL DATA SHEET
<p align="center"> Accessories to bentonite mat EUROBENT CS Bentonite sealing strip: EUROSTRIP </p>	
Properties:	
Composition:	<p align="center"> Natural sodium bentonite Highly molecular polyisobutylen PIB caoutchoc Filler of SiO₂ Filler of CaO Oil Special none toxicological admixtures <i>The raw materials are not toxicological and not unhealthy</i> </p>
Ignition point:	<p align="center">Above 500°C</p>
Density:	<p align="center">1689,81 kg/m³ = 1,69 kg/dm³ = 1,69 g/cm³ (ICAO standard)</p>
Stability and reactivity:	<p align="center"> Swellable in water and any liquid medium Very good stability from 5°C up to 100°C Maximum temperature -5°C up to above 100°C <i>Dimensionary extremely stable, not sticky, not even under conditions of high temperature in summer</i> </p>

EUROSTRIP is not poisonous, not toxically, not unhealthy, not danger or risk for the nature.

Do not eat EUROSTRIP, pay attention with eye contact.

Handing and storage: beware of water, rain. Store the EUROSTRIP in a heated room when temperature is below +5°C.

Poland 58-100 Świdnica, ul. Kliczkowska 42

tel/fax +48 74 857 50 81

www.eurobent.com; office@eurobent.com

IX Wydział Gospodarczy KRS nr 0000297336

Wysokość kapitału zakładowego 50 000,00 zł

NIP 884-26-51-736; REGON 020678548

Sąd Rejonowy dla Wrocławia-Fabrycznej

we Wrocławiu

Deutsche Bank PBC SA

Pl. Grunwaldzki 36, PL-50-364 Wrocław

PL 10 1910 1048 2792 0378 4147 0001 - PLN

PL 80 1910 1048 2792 0378 4147 0002 - EUR

PL 53 1910 1048 2792 0378 4147 0003 - GBP

SWIFT: DEUTPLPK